



AURA[®]

Waterborne Exterior Paint – Satin N631

Features

- Excellent fade resistance and gloss retention
- Proprietary Color Lock[®] Technology for unparalleled color depth
- Substantial film formation starting with the very first coat
- Breathable coating less prone to blistering, providing long-term durability
- Low temperature application down to 35 °F extends the painting season
- Provides a mildew-resistant coating
- Limited Lifetime Warranty
- Engineered with Gennex[®] Color Technology

Recommended For

Recommended for exterior use on wood, fiber cement board, hard board, vinyl and aluminum siding, shakes, unglazed brick, concrete, stucco, cinder block and primed metal.

General Description

A super premium quality, 100% acrylic Exterior Satin. AURA[®] Exterior combines the advantages of our proprietary Color Lock[®] Technology, Gennex[®] Color Technology, and latest resin technology to provide the ultimate exterior coating. Suitable for a variety of exterior substrates to provide a durable long lasting finish with rich colors that resist fading and stand up to rain, snow, wind, and UV damage.

Limitations

- Do not apply when air and surface temperatures are below 35 °F (1.6 °C).
- For Wind-Driven Rain over smooth and stable masonry only (non-elastomeric use). Follow primer/finish instructions.

Product Information

Standard Colors	White (01)	Technical Data	Base 1		
Tint Bases	1X, 2X, 3X & 4X	Vehicle Type	Proprietary 100% Acrylic		
Colorant System	Gennex [®] Waterborne Colorants	Pigment Type	Titanium Dioxide		
Certifications & Qualifications: VOC compliant in all regulated areas The following results are based on independent, third-party laboratory testing: Passes Wind Driven Rain Test (< 0.2) ASTM D6904 1 coat Ultra Spec [®] Masonry Primer N609 2 coats Aura [®] Exterior Satin N631 Passes Alkali Resistance Test (no effect) ASTM D1308 1 coat Ultra Spec [®] Masonry Primer N609 1 coat Aura [®] Exterior Satin N631 Passes Conical Mandrel Flexibility Test (no cracking) ASTM D522 Passes Mildew, Mold Resistance Test (no growth) ASTM D3273/D3274 ASTM D1653 – Water Vapor Transmission Properties – 32.4 perms ASTM D2370 Tensile Properties: Peak Tensile Strength, (psi) 577 Elongation at Break, (%) 130 LIMITED LIFETIME WARRANTY: Benjamin Moore & Co. warrants that this product when used in accordance with the label instructions, will not: 1. blister from properly prepared and primed surfaces, 2. peel from properly prepared and primed surfaces, and 3. wear down or weather to expose the previously painted surface. This warranty shall be effective for so long as you reside in your home and is made to the original residential consumer paint purchaser. This warranty is non-transferable. If this product fails to perform as explained above when used according to label instructions within the warranty period, Benjamin Moore & Co. will, upon presentation of proof of purchase (original sales receipt), provide an equivalent or comparable product at no charge. Since we have no control over surface preparation or application, THIS LIMITED LIFETIME WARRANTY DOES NOT INCLUDE THE COST OF LABOR FOR APPLICATION OF PAINT. BENJAMIN MOORE SHALL IN NO EVENT BE LIABLE FOR INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. SOME STATES DO NOT ALLOW THE EXCLUSION OF INCIDENTAL OR CONSEQUENTIAL DAMAGES, SO THE LIMITATIONS OR EXCLUSIONS CONTAINED IN THE ABOVE WARRANTY MAY NOT APPLY TO YOU. This warranty gives you specific legal rights; you may also have other rights which vary state to state.		Volume Solids	43.1 %		
		Coverage per Gallon at Recommended Film Thickness	250 – 350 Sq. Ft.	Recommended Film Thickness	– Wet 4.6 – 6.3 mils – Dry 2.0 – 2.7 mils
		High Build System Coverage: 160 – 265 sq. ft. 6-10 mils wet film thickness.			
		Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.			
		Dry Time @ 77 °F (25 °C) @ 50% RH	– To Touch 1 Hour – To Recoat 4 Hours	Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times.	
		Dries By	Evaporation, Coalescence		
		Viscosity	100 ± 5 KU		
		Flash Point	None		
		Gloss / Sheen	Satin (20 – 30 @ 60°)		
		Surface Temperature at Application	– Min. 35 °F – Max 100 °F	Thin With See Chart	
Clean Up Thinner	Clean Water				
Weight Per Gallon	11.3 lbs				
Storage Temperature	– Min. 40 °F – Max 90 °F	Volatile Organic Compounds (VOC) 41.4 Grams / Liter 0.34 LBS / Gallon			
Technical Assistance					
Available through your local authorized independent Benjamin Moore retailer. For the location of the retailer nearest you, call 1-866-708-9180 or visit www.benjaminmoore.com					

Surface Preparation

Surfaces must be clean and free of grease, wax, and mildew. Remove any chalk and loose or scaling paint. If previously coated with cement-base waterproofing paints, clean by sandblasting. Glossy surfaces must be dulled. Un-weathered areas such as eaves, ceilings, and overhangs should be washed with a detergent solution and/or rinsed with a strong stream of water from a garden hose to remove contaminants that can interfere with proper adhesion. Stains from mildew must be removed by cleaning with Benjamin Moore® Clean (N318) prior to coating the surface. **Caution:** Refer to the (N318) Clean technical data and material safety data sheets for instructions on its proper use and handling. For metal surfaces, remove rust. Wipe down with paint thinner to remove surface oils.

Difficult Substrates: Benjamin Moore offers a number of specialty primers for use over difficult substrates such as bleeding woods, grease stains, crayon markings, hard glossy surfaces, or other substrates where paint adhesion or stain suppression is a particular problem. Your Benjamin Moore® retailer can recommend the right problem-solving primer for your special needs.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead

Primer/Finish Systems

AURA® Waterborne Exterior Satin is self priming on most properly prepared substrates, including: wood, fiber cement board, hardboard, nonferrous metals and cured masonry surfaces. On bare substrates two coats are required; previously painted surfaces can be finished with 1 or 2 coats.

Special Note: For certain deep colors, a tinted primer must be used to achieve maximum hide and the desired topcoat color. Consult your retailer.

Wood and engineered wood products:

Primer/Finish: 1 or 2 coats AURA® Waterborne Exterior Satin (N631)

Bleeding Type Woods, (Redwood and Cedar):

Primer: Fresh Start® Exterior Deck & Siding Primer (094) or 1-2 coats of Fresh Start® High-Hiding All Purpose (046) may be used.

Finish: 1 or 2 coats AURA® Waterborne Exterior Satin (N631)

Hardboard Siding, Bare or Factory Primed:

Primer/Finish: 1 or 2 coats AURA® Waterborne Exterior Satin (N631)

Vinyl Siding & Vinyl Composite

In most cases, a primer is not necessary. Only areas of pitted and porous vinyl siding must be primed. In these cases, we recommend Fresh Start® High-Hiding All Purpose Primer (046)

Colors that are safe for use on vinyl siding: Do not paint vinyl with any color darker than the original color or having a Light Reflective Value (LRV) of less than 55 unless it is in the Benjamin Moore approved Colors for Vinyl palette and complies with the specific vinyl manufacturer guidelines when making the color selection and painting. Otherwise, the color will absorb more heat, possibly causing the siding to warp, resulting in additional repairs and expenses.

Rough or Pitted Masonry: Poured and precast concrete and block construction should be allowed to cure for at least 30 days. New masonry only needs to be cured for 7 days when using Ultra Spec® Masonry Interior / Exterior 100% Acrylic Masonry Sealer (608). All surfaces must be thoroughly brushed with stiff fiber bristles to remove loose particles.

Primer: Ultra Spec® Masonry Interior/Exterior Hi-Build Block Filler (571)

Finish: 1 or 2 coats AURA® Waterborne Exterior Satin (N631)

Poured or Pre-cast Concrete and Fiber Cement Siding:

Primer/Finish: 1 or 2 coats AURA® Waterborne Exterior Satin (N631)

Masonry, Weathered and Unpainted, Soft with Age (Including Unglazed Brick): Remove any loose, sandy masonry by dry brushing.

Primer: Ultra Spec® Masonry Interior / Exterior 100% Acrylic Masonry Sealer (608)

Finish: 1 or 2 coats AURA® Waterborne Exterior Satin (N631)

Ferrous Metal (Steel and Iron):

Primer: Ultra Spec® HP Acrylic Metal Primer (HP04) or Super Spec HP® Alkyd Metal Primer (P06)

Finish: 1 or 2 coats AURA® Waterborne Exterior Satin (N631)

Non-Ferrous Metal (Galvanized & Aluminum): All new metal surfaces must be thoroughly cleaned with Corotech® Oil & Grease Emulsifier (V600) to remove contaminants. New shiny non-ferrous metal surfaces that will be subject to abrasion should be dulled with very fine sandpaper or a synthetic steel wool pad to promote adhesion

Primer/Finish: 1 or 2 coats AURA® Waterborne Exterior Satin (N631)

Repaint, All Substrates: Prime bare areas with the primer recommended for the substrate above

Application

Use the same application techniques as you would for any low-VOC compliant coating. Use a Benjamin Moore® Premium roller or Premium extra firm nylon polyester brush for best results. AURA® paint features excellent flow and leveling; it's not necessary to over brush to smooth out brush marks. AURA® dries faster than other acrylic paints; avoid lap marks by not painting in direct sunlight and by coating sections of the surface either down or across the structure to natural breaks, maintaining a wet edge. If your edge begins to dry or you see that you missed a spot and the paint is already setting up, allow it to dry completely before touching up that area. This product can also be sprayed.

Spray, Airless

Pressure: 2,000-3,000

psi; Tip: 0.015-0.017

Thinning/Clean up

Conditioning with Benjamin Moore® 518 Extender may be necessary under certain conditions to adjust open time or spray characteristics.

Add 518 Extender or water - Max of 8 fl. oz. to a gallon paint. Never add other paints or solvents.

* Under normal application conditions AURA® may be sprayed to achieve a high build one coat system over properly prepared substrates that are in good condition. Refer to Surface Preparation / Priming Sections for appropriate priming and preparation information.

High Build System Coverage:

160 – 265 sq. ft. 6-10 mils wet film thickness.

Clean up: Wash painting tools in warm soapy water immediately after use. Spray equipment should be given a final rinse with mineral spirits to prevent rusting.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry, empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental Health & Safety Information

WARNING!

Possible birth defect hazard. Contains, **Carbamic acid, 1H-benzimidazol-2-yl-, methyl ester**, which may cause birth defects based on animal data.

Use only with adequate ventilation. Do not breathe vapors, spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. May cause allergic skin reaction. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.

WARNING: This product can expose you to chemicals including Titanium dioxide, which are known to the State of California to cause cancer, and Toluene which are known to the State of California to cause birth defects or other reproductive harm. For more information go to www.P65warnings.ca.gov

WARNING: This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances, even at low levels.

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under **Thinning/Clean up**.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for additional
health and safety information.**